



Preceding designations

Preceding designations of the
aluminium alloys for moulding
corresponding to Spain (UNE)

Europe EN 1706-1998		Spain		
Numerical	Symbolic	Numerical	Symbolic	UNE Standard Cancelled
EN AC-21000	EN AC-Al-Cu4MgTi	L-2140	Al-4CuMgTi	38-214
EN AC-42000	EN AC-AlSi7Mg	L-2651	Al-7SiMg	38-267
EN AC-42100	EN AC-AlSi7Mg0,3	L-2652	Al-7Si0,3Mg	38-241
EN AC-42200	EN AC-AlSi7Mg0,6	L-2653	Al-7Si0,6Mg	38-242
EN AC-43000	EN AC-AlSi10Mg (a)	L-2560	Al-10SiMg	38-256
EN AC-43400	EN AC-AlSi10Mg (Fe)	L-2561	Al-10SiMgFe	38-268
EN AC-44000	EN AC-AlSi11	L-2522	Al-11Si	38-243
EN AC-44100	EN AC-AlSi12 (a)	L-2520	Al-12Si	38-252
EN AC-45000	EN AC-AlSi6Cu4	L-2620	Al-6Si4Cu	38-262
EN AC-45200	EN AC-AlSi5Cu3Mn	L-2610	Al-5Si3Cu	38-261
EN AC-45300	EN AC-AlSi5Cu1Mg	L-2571	Al-5SiCuMg	38-266
EN AC-46000	EN AC-AlSi9Cu3 (Fe)	L-2631	Al-9Si3CuZnFe	38-245
EN AC-46500	EN AC-AlSi9Cu3 (Fe)(Zn)	L-2630	Al-9Si3Cu3ZnFe	38-263
EN AC-47000	EN AC-AlSi12 (Cu)	L-2530	Al-12SiCu	38-253
EN AC-47100	EN AC-AlSi12Cu1 (Fe)	L-2521	Al-12Si1CuFe	38-269
EN AC-48000	EN AC-AlSi12CuNiMg	L-2551	Al-12SiCuNiMg	38-265
EN AC-51000	EN AC-AlMg3 (a)	L-2340	Al-3Mg	38-236
EN AC-71000	EN AC-AlZn5Mg	L-2710	Al-5ZnMg	38-271